

\$SHU72 \$UFKLYLR ,VWLWX]LRQDOH 2SHQ \$FFHV V GHOO 8QLY

5 [e associated chan[es in peripheral airk ay smooth muscle mass of healthy horses

This is the author's manuscript

Original Citation:

Availability:

7KL V YHUVLRQ LKWWSLORRGOHKDQGOH QHW VLQFH 7 =

Published version:

DOI:10.1016/j.tvjl.2017.07.007

Terms of use:

Open Access

\$Q\RRH FDQ IUHHO\ DFFHV V WKH IXOO WH[W RI ZRUNV PDGH DYDLODEOH D
XQGHU D &UHDWLYH &RPPRQV OLFHQVH FDQ EH XVHG DFFRUGLQJ WR WKH
RI DOO RWKHU ZRUNV UHTXLUHV FRQVHQW RI WKH ULJKW KROGHU DXWKR
SURWHFWLRQ E\ WKH DSSOLFDEOH ODZ

(Article begins on next page)

First results on the characterisation of the ancient *folium* dye

Elisa Calà ^(a), Maurizio Aceto ^(a), Aldo Arrais ^(a), Claudio Cassino ^(a), Marco Clericuzio ^(a), Francesco Marsano ^(a), Angelo Agostino ^(b), Gaia Fenoglio ^(b), Monica Gulmini ^(b), Ambra Idone ^(b), Luigi Menghini ^(c), Nicola Di Matteo ^(c) & Lidia Leporini ^(c)

^(a) Dipartimento di Scienze e Innovazione Tecnologica, Università degli Studi del Piemonte Orientale, viale T. Michel, 11 - 15121 Alessandria, Italy

^(b) Dipartimento di Chimica, Università degli Studi di Torino, via P. Giuria, 7 - 10125 Torino, Italy

^(c) Dipartimento di Farmacia, Università "G. d'Annunzio" di Chieti-Pescara, via dei Vestini, 31 - 66013 Chieti, Italy

The *folium* dye, extracted from *Chrozophora tinctoria* (L.) A. Juss., is cited in several ancient treatises as a pictorial material to obtain blue-purple hues (Dodwell 1961; Brunello 1971; Smith & Hawthorne 1974). Therefore its use in painting art must have been common, in particular with main concern to miniature painting. Nevertheless this dye has been rarely identified on artworks (Guineau 1997) possibly due to the lack of diagnostic information. In addition, at present the comprehension of the chemical nature of the dye is almost entirely missing.

In order to fill this lack, in a recent work an improvement of the spectroscopic information concerning *folium* has been proposed (Aceto 2015), allowing to evidence its presence on some Western European manuscripts. The same authors started a study in order to characterise the chemical behaviour of *folium* and to gain information on the structure of the molecules composing it. Preliminary experiments have been carried out in order to verify the reliability of the information emerging from ancient treatises. A relevant feature, always cited in the description of *folium*, is the behaviour of the dye in relation to pH: Theophilus mentions *folium rubeum*, *folium purpureum* and *folium saphireum*, which should be stable in acid, neutral and basic pH, respectively, but this resulted incorrect as the only difference in colour actually derives by the maturation state of the pericarps of *Chrozophora tinctoria* fruits, which yield a blue hue when fruits are unripe (*folium saphireum*) and purple colour with ripe fruits (*folium purpureum*). Moreover, a red solution can be obtained upon addition of Fe³⁺ ions, suggesting that Theophilus' *folium rubeum* could rather be a Fe-*folium* complex. Another surprising feature of *folium* was its behaviour in water and organic solvents. *Folium* is both *hydrophilic*, being very soluble in water, and *hydrophobic*, as the coloured fraction of an aqueous extract can be completely adsorbed on a reversed phase resin. Most probably its molecules have an *amphiphilic* nature, containing both polar and nonpolar functional groups.

Besides these experiments, instrumental analysis was performed with different techniques (HPLC-MS, SERS-Raman, MALDI-ToF-MS, NMR) in order to define the structure of the dye. For simplifying the matrix, a first purification step on a C18 resin was carried out allowing the elimination of uncoloured hydrophilic compounds and the separation of some coloured fractions, among which a yellow and an orange fraction, most probably rich in flavonoids, and some fractions with different purple tones. Hydrolysis with a pectolytic enzyme was then attempted, in order to remove the hydrophilic part of the molecule which is made of oligosaccharides according to NMR analysis. Works are in progress in order to hypothesise chemical structures of the molecules present in the different fractions.

References

- Aceto M., Arrais A., Marsano F., Agostino A., Fenoglio G., Idone A., Gulmini M., A diagnostic study on *folium* and orchil dyes with non-invasive and micro-destructive methods, *Spectrochimica Acta A* 142 (2015) 159-168.
- Brunello F., *De arte illuminandi* (1971) Neri Pozza, Vicenza.
- Dodwell C.R., *Theophilus: the various arts* (1961) Nelson, London.
- Guineau B., Le *folium* des enlumineurs, une couleur aujourd'hui disparue, *Revue d'archéologie médiévale*, 26 (1996) 23-44.
- Smith C.S., Hawthorne J.G., *Mappae Clavicula. A Little Key to the World of Medieval Techniques* (1974) American Philosophical Society, Philadelphia.